

MANUFACTURED BY



1019 SE Holbrook Ct.,
Port St. Lucie, FL 34952
PHONE: 772-335-8225 or 800- 775-9474
FAX: 772-335-3991
EMAIL: sales@enviroseal.com
web: http://enviroseal.com

Duraseal™

**100% Pure Proprietary Acrylic
CONCRETE & BRICK SEALER**

VOC 75% lower than EPA Regulations
Non Toxic - Non Flammable - Non-Hazardous
Environmentally Safe - 100% EPA Compliant
ASTM C-1299

**Eliminates Efflorescence and
Inhibits The Growth
Of Algae , Mold & Bacteria**

SEE DEALER FOR COMPLETE DETAILS

THE FUTURE IS HERE

International Harmonization Schedule "B" No.: 2851.00
United States D.O.T. : Class 55
ENVIROSEAL Lot No.: _____-04___ Date: _____04___

Enviroseal Corporation
Polymeric Acrylic Co-polymer
Specially Formulated For Sealing
All Cement, Stone Brick and
Stucco Surfaces

DIRECTIONS

- Clean the entire surface area with a pressure washer and remove all grease, mud, dirt or foreign matter
 - Acid etch with muriatic acid all trowel or smooth surfaces.
 - Do not apply to concrete less than 14 days old.
 - Do not apply over any kind of silicone based curing agent
- PREVIOUSLY PAINTED OR SEALED CONCRETE**
- Using a high pressure washer remove all old loose paint or sealer from the surface, etch as necessary

APPLICATION

- Apply at temperatures above 45°F
- For best results apply with an airless sprayer, medium Knapp roller or nylon bristle brush
- Duraseal dries in 20 to 40 minutes and completely cures within 24 to 36 hours.
- Re-coating can be done (if necessary) within 4 hours

CLEAN-UP.

- Clean Sprayers, rollers, and brushes in fresh water. Clean hands in soapy water and Boraxo type cleaner. If any Duraseal gets on your clothing it is impossible to remove.

MAINTENANCE

- Occasional cleaning as necessary
- DURASEAL repels acids, oil, water and most alcohol based products. Spills should be removed as soon as possible for safety reasons.
- The molecular adhesive qualities of DURASEAL are unsurpassed.

GUARANTEE: ENVIROSEAL will warrant this product **100%** for three years, no ands ifs or buts.

NOTE: Advanced weathering tests demonstrate this product will remain sealing for an excess of 10 years.

SEE OTHER BROCHURES FOR MSDS AND COVERAGE RATES